


Auxiliaries

AK350 Thinner SRA

Product Description

Blending thinner designed to smooth transition areas from blend-in zones to old paintwork, by dissolving rough overspray area of new and existing finishes. Suitable for panel/spot repair and for clears and topcoats

	Mixing Ratio	This product is ready for use.			
	Spray Guns	HVLP gravity-feed spraygun	1.2–1.3mm	1.8–2.0 bar	10–15 cm
		Conventional gravity-feed spraygun	1.3–1.6mm	3.0–4.0 bar	15–20 cm
	Application	1 mist coat right after the finish, second thin coat in 10-20 seconds.			
	Drying	As recommended for the Dobte clear used.			
Further Treatment		If necessary, minor defects can be sanded out with P2000 paper then polish with any standard fine polishing compound once the clear coat has fully cured.			